

DELO[®]-PUR SJ9356

silane terminated polyurethane | 2C | room-temperature-curing

free of isocyanates, free of silicone | pasty, low transmission, light-blocking | tension-equalizing, flow-resistant, suitable for DELO-AUTOMIX

Special features of product

- compliant with RoHS Directive 2015/863/EU
- component A is humidity-sensitive
- curing can be accelerated at temperatures up to +60 °C

Typical area of use

- -40 - 105 °C
- display bonding
- mixed bondings with plastics
- glass/metal bondings

Curing

Curing time

*until initial strength
at rt approx. +23 °C
tensile shear strength 1 - 2 MPa*

4 h

*until final strength
at rt approx. +23 °C*

7 d

Processing

Mixing ratio A : B - volume

10 : 1

Mixing ratio A : B - weight

10.3 : 1

Processing time after mixing

*in 100 g batch
at rt approx. +23 °C*

9 min

Storage life in unopened original container

at +15 °C to +30 °C

6 month(s)

Technical properties

Color in uncured condition

black

Filler particle type


minerals

Density of component A	1.31	g/cm ³
Density of component B	1.28	g/cm ³

Parameters


Tensile shear strength <i>Based on DIN EN 1465 Al Al Pretreatment: sand-blasted at approx. +23 °C 7 d</i>	3	MPa
Peel resistance <i>DELO Standard 38 Steel Steel Pretreatment: sand-blasted at approx. +23 °C 7 d</i>	4	N/mm
Tensile strength <i>Based on DIN EN ISO 527 at approx. +23 °C 7 d</i>	2	MPa
Elongation at tear <i>Based on DIN EN ISO 527 at approx. +23 °C 7 d</i>	120	%
Young's modulus <i>Based on DIN EN ISO 527 at approx. +23 °C 7 d</i>	< 10	MPa
Shore hardness A <i>Based on DIN EN ISO 868 at approx. +23 °C 7 d</i>	51	
Glass transition temperature <i>DMTA at approx. +23 °C 7 d</i>	< -50	°C
Shrinkage <i>DELO Standard 13 at approx. +23 °C 7 d</i>	2	vol. %
Water absorption <i>Based on DIN EN ISO 62 at approx. +23 °C 7 d Type of storage: Desiccator Duration: 72 h</i>	0.8	wt. %
Decomposition temperature <i>DELO Standard 36</i>	236	°C

Substrates: Al/Al, based on DIN EN 1465



at room temperature (approx. 23°C)

Tensile shear strength measured at stated temperatures



Substrates: Al / Al

Converting table

°F	= (°C x 1.8) + 32	1 MPa	= 145.04 psi
1 inch	= 25.4 mm	1 GPa	= 145.04 ksi
1 mil	= 25.4 µm	1 cP	= 1 mPa·s
1 oz	= 28.3495 g	1 N	= 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Unless otherwise specified, the values were measured after 168 h at approx. 23 °C / 50 % r. h., and the values of heat-cured samples were measured after 24 h at approx. 23 °C / 50 % r. h.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

You can find further details in the instructions for use.

The instructions for use are available on www.DELO-adhesives.com.
We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT